

8OZ GEOTEXTILE

STYLE 801 - 8 OZ NON-WOVEN GEOTEXTILE			
Property	Test Method	Minimum Average Roll Value ENGLISH	Minimum Average Roll Value METRIC
Grab Tensile	ASTM D 4632	203 lb.	0.9 kN
Grab Elongation	ASTM D 4632	50%	50%
Mullen Burst	ASTM D 3786	380 psi	2619 kPa
Puncture	ASTM D 4833	120 lb.	0.533 kN
Trapezoid Tear	ASTM D 4533	80 lb.	0.355 kN
UV Resistance	ASTM D 4355	70%@500 hrs	70%@500 hrs
AOS	ASTM D 4751	80 sieve	0.15 mm
Permittivity	ASTM D 4491	1.5 sec ⁻¹	1.5 sec ⁻¹
Flow Rate	ASTM D 4491	110 gal/min/ft ²	4470 L/min/m ²