



BTL™-12 String Reinforced

Black / White

LOW TEMPERATURE - HYDROCARBON STABLE

DESCRIPTION	12 X 12 COUNT PER INCH	
FABRICATION & WAREHOUSE	PRINEVILLE, OREGON	
WEIGHT	53.5 lbs (+/-5%)	ASTM D 751
THICKNESS	10.2 MILS (+/-10%)	ASTM D 5199
PEEL	76.2 oz	ASTM D 1876
1" Elongation at Break MD/TD	643.8% / 750.0 %	
1" Load at Yield MD/TD	24.8 lbf / 25.8 lbf	ASTM D 882
1" Load at Break MD/PSI	28 lbf / 2742.5 psi	ASTM D 882
1" Load at Break TD/PSI	27.7 lbf / 2713.3 psi	ASTM D 882
3" Load at Yield MD/PSI	76.8 lbf / 118.3 lbf	ASTM D 882
3" Load at Break MD/PSI	74.6 lbf / 2436.7 psi	ASTM D 882
3" Load at Break TD/PSI	75.2 lbf / 2456.9 psi	ASTM D 882
3" Elongation at Break MD/TD	611.3% / 759.3%	
Tongue Tear	20.8 lbf / 25.4lbf	ASTM D 2261
Trapezoidal Tear	30.2 lbf / 43.7 lbf	ASTM D 4533
PPT Resistance MD/TD	36.7 lbf / 26.8 lbf	ASTM D 2582